

**Title:**

CLASSIFICATION OF REACTION TO FIRE  
PERFORMANCE  
IN ACCORDANCE WITH  
EN 13501-1:2018.

**Notified Body No:**

0833

**Product Name:**

"Alideck"  
("PD712895MRT.90 - Beige Metallic Speckle")

**Report No:**

WF 423540

**Issue No:**

2

**Prepared for:**

**Canoports UK Ltd**  
T/A Milwood Group  
27 Rochester Airport Industrial Est.  
Laker Road  
Rochester  
Kent  
ME1 3QX

**Date:**

4<sup>th</sup> February 2020

## 1. Introduction

This classification report defines the classification assigned to “Alideck” (“PD712895MRT.90 - Beige Metallic Speckle”), a coated aluminium decking board, in accordance with the procedures given in EN 13501-1:2018.

## 2. Details of classified product

### 2.1 General

The product, “Alideck” (“PD712895MRT.90 - Beige Metallic Speckle”), is defined as being suitable for floorcovering applications.

### 2.2 Product description

The product, “Alideck” (“PD712895MRT.90 - Beige Metallic Speckle”), is fully described below and in the test reports provided in support of classification listed in Clause 3.1.

General description		Aluminium decking board
Product reference		“Alideck”
Name of manufacturer		Milwood Group
Profile thickness		30mm (stated by sponsor) 29.98mm (determined by <a href="#">Warringtonfire</a> )
Profile weight per unit area		17.68kg/m <sup>2</sup> (determined by <a href="#">Warringtonfire</a> )
Coating	Generic type	Polyester powder coating
	Product reference	“PD712895MRT.90”
	Name of manufacturer	Sherwin Williams Syntha Pulvin
	Colour reference	“Beige Metallic Speckle”
	Number of coats	One
	Application thickness	60 – 80µm
	Application rate	84g/m <sup>2</sup>
	Density / specific gravity	<b>See Note 1 Below</b>
	Application method	Electrostatic spray
	Curing process	Heated at 180°C for 10 minutes
	Flame retardant details	<b>See Note 2 Below</b>
Substrate	Generic type	Aluminium extrusion
	Product reference	“Alideck”
	Name of manufacturer	Milwood Group
	Thickness	1.5mm (profile thickness 30mm)
	Weight per unit area	1.865kg/m <sup>2</sup>
	Colour reference	“Silver”
Flame retardant details	<b>See Note 2 Below</b>	
Brief description of manufacturing process		Extruded profile

**Note 1:** The sponsor was unable to provide this information.

**Note 2:** The sponsor of the test has confirmed that no flame retardant additives were utilised in the production of the product.

### 3. Test reports & test results in support of classification.

#### 3.1 Test reports.

Name of Laboratory	Name of sponsor	Test reports/extended application report Nos.	Test method / extended application rules & date
warringtonfire	Canoports UK Ltd T/A Milwood Group	WF 418172	EN ISO 1716
		WF 418524	EN ISO 1716 (Summary report)
		WF 423488	EN ISO 9239-1

#### 3.2 Test results

Test method & test number	Parameter	No. tests	Results	
			Continuous parameter - mean (m)	Compliance parameters
EN ISO 9239-1	Critical flux	3	$\geq 11.0 \text{ kW/m}^2$	Compliant
	Smoke		1.53 %min	Compliant
EN ISO 1716	Coating - PCS (b)	3	1.3685 MJ/m <sup>2</sup>	Compliant
	Aluminium - PCS (a)	Deemed to satisfy (0.00)		Compliant
	For the product as a whole PCS (d)	Summary result	0.7022 MJ/Kg	Compliant

#### 4. Classification and field of application

##### 4.1 Reference of classification

This classification has been carried out in accordance with clause 9 of EN 13501-1:2018.

##### 4.2 Classification

The product, "Alideck" ("PD712895MRT.90 - Beige Metallic Speckle") a coated aluminium decking board, in relation to its reaction to fire behaviour is classified:

**A2<sub>FL</sub>**

The additional classification in relation to smoke production is:

**s1**

The format of the reaction to fire classification for floorings is:

Fire Behaviour		Smoke Production	
A2 <sub>FL</sub>	-	s	1

i.e. A2<sub>FL</sub> – s1

**Reaction to fire classification: A2<sub>FL</sub> – s1**

##### 4.3 Field of application

This classification is valid for the following end use applications:

- i) Floorcovering applications

This classification is also valid for the following product parameters:

Product thickness	No variation allowed
Product weight per unit area	No variation allowed
Coating application rate	No variation allowed
Coating thickness	No variation allowed
Coating composition	No variation allowed
Product construction	No variation allowed

## 5. Limitations


This document does not represent type approval or certification of the product.

### SIGNED



.....  
**Matthew Dale**  
Principal Certification Engineer  
Technical Department

### APPROVED



.....  
**Janet Murrell**  
Technical Manager  
Technical Department  
on behalf of **warringtonfire**

Issue No : 2	Issue Date: 14 <sup>th</sup> February 2020
Revised By: M Dale	Approved By: J Murrell
Reason for Revision: This document replaces Issue 1 (dated 4 <sup>th</sup> February 2020) of the same number which has been withdrawn. The ISO 1716 test data and references have been corrected and the address of the sponsor has been corrected.	

This copy has been produced from a .pdf format electronic file that has been provided by Warringtonfire to the sponsor of the report and must only be reproduced in full. Extracts or abridgements of reports must not be published without permission of Warringtonfire. The pdf copy supplied is the sole authentic version of this document. All pdf versions of this report bear authentic signatures of the responsible Warringtonfire staff.

This report may only be reproduced in full. Extracts or abridgements of reports shall not be published without permission of Warringtonfire. All work and services carried out by Warringtonfire Testing and Certification Limited are subject to, and conducted in accordance with, the Standard Terms and Conditions of Warringtonfire Testing and Certification Limited, which are available at <https://www.element.com/terms/terms-and-conditions> or upon request.